



Domnita Ancuta nr 8, Sector 1, Bucharest Tel./Fax: 0040 01 312 56 60, E-mail: office@tehnicaldent.ro  
IBAN: RO17 RNCB 0068 0043 7192 0001 Nr. Inreg. Reg. Com.: J/09/137/99, Cod fiscal: RO 117 58 273

---

## Bio-C Temp 2g

**Pret:**

**178,50 lei TVA inclusa**



### **Descriere produs:**

Bio-C Temp - pasta bioceramica pentru pansamente intracanal

### **Avantaje**

Elibereaza gradual ioni de calciu ( $Ca^{2+}$ ) - nu necesita schimbare periodica

Biocompatibila

Alcalinitate ridicata (pH~12) - mediu neadecvat cresterii bacteriilor

Usor de indepartat - timp de lucru optimizat

Radio-opacitate ridicata - vizualizare radiografica excelenta

### **Indicatii**

Medicatie intracanal in tratamentul endodontic al dintilor cu necroza pulpara si retratamente



Domnita Ancuta nr 8, Sector 1, Bucharest Tel./Fax: 0040 01 312 56 60, E-mail: office@tehnicaldent.ro  
IBAN: RO17 RNCB 0068 0043 7192 0001 Nr. Inreg. Reg. Com.: J/09/137/99, Cod fiscal: RO 117 58 273

---

Medicatie intracanal in cazul perforarilor, resorbtiilor interne si externe, inainte de utilizarea Bio-C Repair, MTA Repair HP sau MTA Angelus

Medicatie intracanal pentru cazurile de rizogeneza incompleta

### **Date tehnice**

pH:~12

Radio-opacitate:  $\geq 9\text{mm Al}$

Dimensiune particula:  $\leq 2\mu\text{m}$

Grosime pelicula:  $\sim 20\mu\text{m}$

Fluiditate:  $\sim 25\text{mm}$

Solubilitate:  $\sim 1.0\%$  (conform ISO6876 Adapted)

### **Compozitie**

Silicat tricalcic(C3S)

Silicat dicalcic (C2S)

Aluminat tricalcic

Oxid de calciu

Ester salicilat

Tungstat de calciu

Polietilen glicol

Oxid de titan

### **Prezentare**

Bio-C Temp - 2g



Domnita Ancuta nr 8, Sector 1, Bucharest Tel./Fax: 0040 01 312 56 60, E-mail: office@tehnicaldent.ro  
IBAN: RO17 RNCB 0068 0043 7192 0001 Nr. Inreg. Reg. Com.: J/09/137/99, Cod fiscal: RO 117 58 273

---